

DESCRIPTION

Smooth, velvety Faux Suede Patches are lasered, providing contrasting, engraved detail to your design while maintaining the velvety feel on your fingertips. Available in 23 colours.

PATCH SIZE LIMITS

Area - Min .5" x .5"
Max 6.0" x 6.0"

Due to the laser cutting process, patch size may vary by +/- 2%.

TEXT AND ELEMENTS

Minimum elements: .5mm wide
Minimum text size: 2mm height

COLOUR

23 colours available

BACKING

Faux Suede Patches are available with Heat Applied or Pressure Sensitive backing.

BORDER

Faux Suede Patches are available without a border, or you can choose to add an overlock stitched border.

The optional overlock border size is 4mm +/- 1mm.

ELECTRONIC PROOF

Digital sample will be sent via email. Edits are allowed - charges may apply.

PRE-PRODUCTION SAMPLE

Pre-production sample is available for fee.

WASHING INFORMATION

Faux Suede Patches will withstand up to 25 domestic washing machine cycles.

SHELF LIFE

To maximize the shelf life of this product please keep at room temperature.



HEAT APPLY WITH A PROFESSIONAL HEAT PRESS

HOTRONIX® 360 IQ® HAT PRESS

Time: 15-20 seconds

Temp: 280°F Upper / 320°F Lower

Pressure: Medium

Cover Sheet: 1/8" Foam Pad

HEATED UPPER PLATEN

Time: 15-20 seconds

Temp: 360° F

Pressure: Medium

Cover Sheet: FlexStyle® Silicone Pad or 1/8" Foam Pad

- Pre-heat bottom platen for 60 seconds and fabric for 20 seconds.

HEATED LOWER PLATEN

Time: 15-20 seconds

Temp: 280°F Upper / 320°F Lower

Pressure: Medium

Cover Sheet: FlexStyle® Silicone Pad or 1/8" Foam Pad

- For best results, Stahls' recommends applying with a heated lower platen.

CAP PRESS

Time: 20-30 seconds

Temp: 360°F

Pressure: Medium

Cover Sheet: FlexStyle® Silicone Pad or 1/8" Foam Pad

Instructions: Pre-heat the lower platen for 60 seconds. Load cap and pre-heat 20 seconds. Cover with Flex Pad and press.

FABRIC COMPATIBILITY

Heat Applied:

- 100% Cotton
- 100% Polyester
- Cotton/Poly Blends

Pressure Sensitive:

- Smooth surfaces on hard goods

SPECIAL NOTES

- On a Hotronix Heat Press, the pressure will come to a 7 when using a silicone pad

PRESSURE SENSITIVE APPLICATION

PRESSURE-SENSITIVE (STICKER) APPLICATION

- Make sure the application area is thoroughly cleaned. Rubbing alcohol can be used.
- Remove paper backing and press firmly on the desired location.
- For best results, please allow at least 24 hours cure time.

FOR USE ON

Smooth, hard surfaces. Not recommended for surfaces that may contain an oil finish such as silicone or any type of outdoor goods.